



TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %10 CV-%90 PES 30 GSM PLAIN

Technical Characteristics	Analysis Method	Unit		Average values		Individual values
				Target	Tolerance	Tolerance
Composition	-	%		%10 Cv	min. 8 max. 12	-
				%90 Pes	min. 88 max. 92	-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		30	± %10	±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,50	min. 0,40 max. 0,60	min. 0,35 max. 0,65
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	60	min. 48	min. 42
		N \ 50 mm	CD	17	min. 14	min. 12
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	50	max. 60	max. 70
		%	CD	170	max. 210	max. 230
Tensile Strength at break (Wet)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	54	min. 43	min. 38
		N \ 50 mm	CD	15	min. 12	min. 11
Breaking Elongation (Wet)	WSP 110.4 (ERT 20.2-89)	%	MD	60	max. 70	max. 80
		%	CD	160	max. 200	max. 220
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050,00	min. 1000,00	max. 2000,00
TOTAL BACTERIA	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
MOLDS AND YEASTS	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
TOTAL E.COLI/COLIFORM	USP 61 EP 2.6.12	CFU/gr		0		0

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager

ENDER NONWOVEN®

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ

4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep

Tel: 0 342 337 29 29 | 337 23 83 (Pbx)

Faks: 0 342 337 12 29