



## TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %20COPET %80PES 47 GSM APERTURED

Technical Characteristics	Analysis Method	Unit		Average values		Individual values
				Target	Tolerance	Tolerance
Composition	-	%		%20 Copet	min. 16 max. 24	-
				%80 Pes	min. 76 max. 84	-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m <sup>2</sup>		47	± %10	±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,52	min. 0,42 max. 0,62	min. 0,37 max. 0,67
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	140	min. 112	min. 98
		N \ 50 mm	CD	32	min. 26	min. 22
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	35	max. 45	max. 55
		%	CD	150	max. 190	max. 210

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm. The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date  
13.04.2023

Prepared By  
İsrafil TORUNTAY  
Quality Chief

Approved By  
Adnan ÖZBİLİCİ  
Quality Manager

 **ENDER NONWOVEN®**

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ  
4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep  
Tel: 0 342 337 29 29 | 337 23 83 (Pbx)  
Faks: 0 342 337 12 29