



TECHNICAL DATA SHEET

Product Name

SPUNLACED NONWOVEN FABRIC // %100 PES 60 GSM PLAIN

Technical Characteristics	Analysis Method	Unit		Average values		Individual values
				Target	Tolerance	Tolerance
Composition	-	%		-	min. -	-
				%100 Pes	max. -	-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		60	± %10	±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,69	min. 0,59 max. 0,79	min. 0,54 max. 0,84
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	140	min. 112	min. 98
		N \ 50 mm	CD	34	min. 27	min. 24
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	50	max. 60	max. 70
		%	CD	180	max. 220	max. 240
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050,00	min. 1000,00	max. 2000,00
TOTAL BACTERIA	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
MOLDS AND YEASTS	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
TOTAL E.COLI/COLIFORM	USP 61 EP 2.6.12	CFU/gr		0		0

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager

 **ENDER NONWOVEN**®

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ
4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep
Tel: 0 342 337 29 29 | 337 23 83 (Pbx)
Faks: 0 342 337 12 29