



TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %100 CV 48 GSM DOT

Technical Characteristics	Analysis Method	Unit		Average values			Individual values	
				Target	Tolerance		Tolerance	
Composition	-	%		%100 Cv	min.	-	-	
					max.	-	-	
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		48	± %10		±%10	
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,60	min.	0,50	min.	0,45
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	65	min.	52	min.	46
		N \ 50 mm	CD	17	min.	14	min.	12
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	35	max.	45	max.	55
		%	CD	110	max.	140	max.	160
Tensile Strength at break (Wet)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	33	min.	26	min.	23
		N \ 50 mm	CD	9	min.	7	min.	6
Breaking Elongation (Wet)	WSP 110.4 (ERT 20.2-89)	%	MD	40	max.	50	max.	60
		%	CD	100	max.	130	max.	150
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050,00	min.	1000,00	max.	2000,00
TOTAL BACTERIA	USP 61 EP 2.6.12	CFU/gr		≤10				≤100
MOLDS AND YEASTS	USP 61 EP 2.6.12	CFU/gr		≤10				≤100
TOTAL E.COLI/COLIFORM	USP 61 EP 2.6.12	CFU/gr		0				0

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager

ENDER NONWOVEN®

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ
4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep
Tel: 0 342 337 29 29 | 337 23 83 (Pbx)
Faks: 0 342 337 12 29