



TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %15COPET %85PES 50 GSM APERTURED

Technical Characteristics	Analysis Method	Unit		Average values		Individual values
				Target	Tolerance	Tolerance
Composition	-	%		%15 Copet	min. 12 max. 18	-
				%85 Pes	min. 82 max. 88	-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		50	± %10	±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,55	min. 0,45 max. 0,65	min. 0,40 max. 0,70
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	130	min. 104	min. 91
		N \ 50 mm	CD	30	min. 24	min. 21
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	35	max. 45	max. 55
		%	CD	150	max. 190	max. 210

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager

 **ENDER NONWOVEN®**

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ
4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep
Tel: 0 342 337 29 29 | 337 23 83 (Pbx)
Faks: 0 342 337 12 29