



TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %100 PES 30 GSM PLAIN THIN

Technical Characteristics	Analysis Method	Unit		Average values			Individual values
				Target	Tolerance		Tolerance
Composition	-	%		-	min.	-	-
			%100 Pes	max.	-	-	
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		30	± %10	±%10	
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,35	min. 0,25 max. 0,45	min. 0,20 max. 0,50	
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	70	min. 56	min. 49	
		N \ 50 mm	CD	18	min. 14	min. 13	
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	40	max. 50	max. 60	
		%	CD	160	max. 200	max. 220	
Hot Shrinkage	200°C- 3 minute	%	MD	6	max. 8	max. 10	
		%	CD	3	max. 5	max. 8	

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less than 1000 mm. The tolerance for width is ± 10 mm for high than 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager

ENDER NONWOVEN®

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ

4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep

Tel: 0 342 337 29 29 | 337 23 83 (Pbx)

Faks: 0 342 337 12 29