

Product Name : **SPUNLACED NONWOVEN FABRIC // %10 CV-%90 PES 40 GSM DOT**

<u>Technical Characteristics</u>	<u>Analysis Method</u>	<u>Unit</u>		<u>Average values</u>		<u>Individual values</u>
				Target	Tolerance	Tolerance
Composition	-	%		%10 Cv	min. 8 max. 12	-
				%90 Pes	min. 88 max. 92	-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		40	± %10	±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,66	min. 0,56 max. 0,76	min. 0,51 max. 0,81
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	65	min. 52	min. 46
		N \ 50 mm	CD	17	min. 14	min. 12
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	50	max. 60	max. 70
		%	CD	170	max. 210	max. 230
Tensile Strength at break (Wet)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	59	min. 47	min. 41
		N \ 50 mm	CD	15	min. 12	min. 11
Breaking Elongation (Wet)	WSP 110.4 (ERT 20.2-89)	%	MD	60	max. 70	max. 80
		%	CD	160	max. 200	max. 220
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050,00	min. 1000,00	max. 2000,00
TOTAL BACTERIA	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
MOLDS AND YEASTS	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
TOTAL E.COLI/COLIFORM	USP 61 EP 2.6.12	CFU/gr		0		0

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager



ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ

4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep

Tel: 0 342 337 29 29 | 337 23 83 (Pbx)

Faks: 0 342 337 12 29