



## TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %100 CV 70 GSM DOT

Technical Characteristics	Analysis Method	Unit		Average values		Individual values
				Target	Tolerance	Tolerance
Composition	-	%		%100 Cv	min. - max. -	-
						-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m <sup>2</sup>		70	± %10	±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,73	min. 0,63 max. 0,83	min. 0,58 max. 0,88
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	105	min. 84	min. 74
		N \ 50 mm	CD	26	min. 21	min. 18
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	35	max. 45	max. 55
		%	CD	110	max. 140	max. 160
Tensile Strength at break (Wet)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	53	min. 42	min. 37
		N \ 50 mm	CD	13	min. 10	min. 9
Breaking Elongation (Wet)	WSP 110.4 (ERT 20.2-89)	%	MD	40	max. 50	max. 60
		%	CD	100	max. 130	max. 150
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050,00	min. 1000,00	max. 2000,00
TOTAL BACTERIA	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
MOLDS AND YEASTS	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
TOTAL E.COLI/COLIFORM	USP 61 EP 2.6.12	CFU/gr		0		0

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date  
13.04.2023

Prepared By  
İsrafil TORUNTAY  
Quality Chief

Approved By  
Adnan ÖZBİLİCİ  
Quality Manager

 **ENDER NONWOVEN**®

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ  
4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep  
Tel: 0 342 337 29 29 | 337 23 83 (Pbx)  
Faks: 0 342 337 12 29