



TECHNICAL DATA SHEET

Product Name :

SPUNLACED NONWOVEN FABRIC // %100 PES 35 GSM PLAIN

Technical Characteristics	Analysis Method	Unit		Average values		Individual values
				Target	Tolerance	Tolerance
Composition	-	%		-	min. -	-
				%100 Pes	max. -	-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		35	± %10	±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,54	min. 0,44 max. 0,64	min. 0,39 max. 0,69
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	70	min. 56	min. 49
		N \ 50 mm	CD	20	min. 16	min. 14
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	50	max. 60	max. 70
		%	CD	180	max. 220	max. 240
TOTAL BACTERIA	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
MOLDS AND YEASTS	USP 61 EP 2.6.12	CFU/gr		≤10		≤100
TOTAL E.COLI/COLIFORM	USP 61 EP 2.6.12	CFU/gr		0		0

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager



ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ

4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep

Tel: 0 342 337 29 29 | 337 23 83 (Pbx)

Faks: 0 342 337 12 29