



TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %100 CV 42 GSM APERTURED

Technical Characteristics	Analysis Method	Unit		Average values			Individual values
				Target	Tolerance		Tolerance
Composition	-	%		%100 Cv	min.	-	-
					max.	-	-
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		42	± %10		±%10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,48	min.	0,38	min. 0,33
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	55	min.	44	min. 39
		N \ 50 mm	CD	15	min.	12	min. 11
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	35	max.	45	max. 55
		%	CD	110	max.	140	max. 160
Tensile Strength at break (Wet)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	28	min.	22	min. 19
		N \ 50 mm	CD	8	min.	6	min. 5
Breaking Elongation (Wet)	WSP 110.4 (ERT 20.2-89)	%	MD	40	max.	50	max. 60
		%	CD	100	max.	130	max. 150
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050,00	min.	1000,00	max. 2000,00
TOTAL BACTERIA	USP 61 EP 2.6.12	CFU/gr		≤10			≤100
MOLDS AND YEASTS	USP 61 EP 2.6.12	CFU/gr		≤10			≤100
TOTAL E.COLI/COLIFORM	USP 61 EP 2.6.12	CFU/gr		0			0

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager

ENDER NONWOVEN®

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ

4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep

Tel: 0 342 337 29 29 | 337 23 83 (Pbx)

Faks: 0 342 337 12 29