



TECHNICAL DATA SHEET

Product Name : SPUNLACED NONWOVEN FABRIC // %10 CV-%90 PES 50 GSM APERTURED

| Technical Characteristics | Analysis Method | Unit | | Average values | | Individual values |
|---------------------------------|-------------------------|------------------|----|----------------|------------------------|------------------------|
| | | | | Target | Tolerance | Tolerance |
| Composition | - | % | | %10 Cv | min. 8 max. 12 | - |
| | | | | %90 Pes | min. 88 max. 92 | - |
| Basis Weight | WSP 130.1 (ERT 40.3-90) | g/m ² | | 50 | ± %10 | ±%10 |
| Thickness | WSP 120.6 (ERT 30.5-99) | mm | | 0,63 | min. 0,53 max. 0,73 | min. 0,48 max. 0,78 |
| Tensile Strength at break (Dry) | WSP 110.4 (ERT 20.2-89) | N \ 50 mm | MD | 90 | min. 72 | min. 63 |
| | | N \ 50 mm | CD | 24 | min. 19 | min. 17 |
| Breaking Elongation (Dry) | WSP 110.4 (ERT 20.2-89) | % | MD | 50 | max. 60 | max. 70 |
| | | % | CD | 170 | max. 210 | max. 230 |
| Tensile Strength at break (Wet) | WSP 110.4 (ERT 20.2-89) | N \ 50 mm | MD | 81 | min. 65 | min. 57 |
| | | N \ 50 mm | CD | 22 | min. 17 | min. 15 |
| Breaking Elongation (Wet) | WSP 110.4 (ERT 20.2-89) | % | MD | 60 | max. 70 | max. 80 |
| | | % | CD | 160 | max. 200 | max. 220 |
| Liquid Absorbtion Capacity | WSP 010.1 (ERT 10.3-99) | % | | 1050,00 | min. 1000,00 | max. 2000,00 |
| TOTAL BACTERIA | USP 61 EP 2.6.12 | CFU/gr | | ≤10 | | ≤100 |
| MOLDS AND YEASTS | USP 61 EP 2.6.12 | CFU/gr | | ≤10 | | ≤100 |
| TOTAL E.COLI/COLIFORM | USP 61 EP 2.6.12 | CFU/gr | | 0 | | 0 |

The width of the reel is measured on the reel. The tolerance for width is ± 5 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date
13.04.2023

Prepared By
İsrafil TORUNTAY
Quality Chief

Approved By
Adnan ÖZBİLİCİ
Quality Manager

ENDER NONWOVEN®

ENDER NONWOVEN TEKSTİL SANAYİ VE TİCARET ANONİM ŞİRKETİ

4.Org. San. Böl. 83412 Nolu Cd. No: 1 Şehitkamil/Gaziantep

Tel: 0 342 337 29 29 | 337 23 83 (Pbx)

Faks: 0 342 337 12 29